## Technical Specification of Ink ECOO-IN-C



< 8-10

< 8-10

>30

>30

Туре	ECOO-IN-C										
	Printing speed: 12000rph-15000rph										
		Environment friendly									
Features		Anti-skinning performance									
		Good water/ink balance									
		Rich in printing layer									
	Clear and complete in printing dots										
		Quick-drying performance, quick setting, quick turn									
Packing		1kg/vacuum tin, 12tins/carton									
Shelf Life	3 years(from the production date); product against light and water										
	ECOO-II	ECOO-IN-C printing ink is developed by the latest European technology system. It is made from									
	polymeric	polymeric, high-soluble resin and newly-invented paste pigment. This product is suitable for printing									
Application	packaging, advertisement, label, high-quality brochures and decorative products on art paper, coated										
	paper, offset paper, cardboard, etc., especially suitable for medium and high-speed printing.										
ITEM/TYPE	TACK	FLUIDITY	PARTICLE	GLOSS	SETTING	DRYING	SKINNING				
	VALUE	(mm)	SIZE (µm)		TIME (min)	TIME (hr)	TIME (hr)				
С	8-9	39±1	12.5	85	4	< 8-10	>30				
YELLOW											
С	8.5-9.5	40±1	12.5	75	4	< 8-10	>30				
MAGENTA											

BLACK								
Tack Value	The value is measured in 1 minute by inkometer at 32 $^{\circ}\mathrm{C}^{\circ}$ and 400rpm.							
Set Time	Printing adapter, 157g art paper, the volume of ink-coating can be up to 0.125cc							
Condition of test	Room temperature 25 °C , humidity 65%-75%							

75

80

12.5

12.5

ITEM/TYPE	Light	Heat	Acid	Alkaline	Alcohol	Soap		
	Resistance	Resistance	Resistance	Resistance	Resistance	Resistance		
С	3-4	5	5	4	4	4		
YELLOW								
С	3-4	5	5	5	4	5		
MAGENTA								
С	6-7	5	5	5	5	5		
CYAN								
С	6-7	5	5	5	5	5		
BLACK								
Light Fastness	1-8 (weak-strong)							
Others	1-5 (weak-strong)							

Hangzhou EcooGraphix Digital Technology Co, Ltd.

8.5-9.5

9-10

39±1

38±1

C

**CYAN** 

Add: Room 708, Tianheng Building, No.1509, Binsheng Rd, Binjiang District, Hangzhou, China

Tel: 0086 571-87391001 Fax:0086 0571-81391066

E-mail:info@ecoographix.com Website: www.ecoographix.com